



SLIP RESISTANCE TEST REPORT

Client: Middle Earth Tiles
Client's Reference: Guy Roberts

Tested By: Kevin Stackhouse
Date: 05/04/2007

DESCRIPTION OF SAMPLE

Manufacturer: Middle Earth Tiles
Common Name: Terracotta
Specimen Size: 300mm x 300mm
No. of Specimens Tested: FIVE

Material Type: Clay and Sand
Surface Type: Un-glazed
Surface Coating: Nil

METHOD

Tests were carried out in accordance with AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces, Part 1- Requirements, Appendix A "Method for the Measurement of the Coefficient of friction of Wet Surfaces".

Type of Test: Fixed

Location of Test: Safety Step workshop

Air Temperature: 20°C

SLOPE:

RESULTS

Specimen No.	Dilution Ratio	WET/DRY	Mean Coefficient of Friction
one		Wet	0.76
two		Wet	0.74
three		Wet	0.71
four		Wet	0.75
five		Wet	0.72

SAMPLE MEAN COEFFICIENT OF FRICTION: 0.74

REQUIREMENTS

Horizontal Surfaces: When tested in accordance with the method set out in Appendix A, the pedestrian surface shall have a mean coefficient of friction of not less than **0.40** and no specimen in that sample shall be less than **0.35**.

SAFETY STEP (NZ) LTD

THE ULTIMATE IN ANTI-SLIP AND WAY FINDING SYSTEMS

VISIT SAFETY STEP ON www.safetystep.com

MIDDLE EARTH TILES NEW ZEALAND

136 Great North Road, Grey Lynn | 60 Hudson Rd, Warkworth
sales@middleearthtiles.co.nz | www.middleearthtiles.co.nz